

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau




(43) International Publication Date
22 July 2004 (22.07.2004)

PCT

(10) International Publication Number
WO 2004/060328 A1

- (51) International Patent Classification⁷: **A61K 6/06**, C03C 10/00 (72) Inventor: **BRODKIN, Dmitri**; 75 Herbert Terrace, West Orange, NJ 07052 (US).
- (21) International Application Number: PCT/US2003/033018 (74) Agent: **KNAB, Ann, M.**; Pentron Corporation, 53 North Plains Industrial Road, Wallingford, CT 06492 (US).
- (22) International Filing Date: 17 October 2003 (17.10.2003) (81) Designated State (national): **MX**.
- (25) Filing Language: English (84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).
- (26) Publication Language: English
- (30) Priority Data:
60/436,202 23 December 2002 (23.12.2002) US
10/646,171 22 August 2003 (22.08.2003) US
- Published:
— with international search report
- (71) Applicant: **PENTRON LABORATORY TECHNOLOGIES, LLC** [US/US]; 53 North Plains Industrial Road, Wallingford, CT 06492-0724 (US).
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PRESSABLE GLASS-CERAMICS WITH TEXTURED MICROSTRUCTURE



(57) Abstract: A pressable dental ceramic comprising a mixture of glass and glass-ceramic frits. A refractory filler is also combined with the frits. The dental ceramic contains an amount of leucite less than about 35 percent by weight. Other additives may be included such as pigments, opacifying agents and fluorescing agents. The dental ceramic comprises a cellular-like microstructure comprised of glassy regions surrounded by clusters of leucite crystals distributed around those glassy regions forming a cellular three-dimensional network.

WO 2004/060328 A1

THIS PAGE BLANK (USPTO)

Pressable Glass-Ceramics With Textured Microstructure

5 Cross-Reference to Related Applications:

This application claims priority to U.S. Patent Application No. 10/646,171, filed on August 22, 2003, and to U.S. Provisional Application No. 60/436,202, filed December 23, 2002, both of which are incorporated herein by reference.

10 Field Of Invention

This invention relates generally to glass-ceramics comprising leucite and more specifically to glass-ceramics for use in the manufacture of dental restorations and methods of manufacture thereof.

15 Background Of The Invention

High-strength feldspathic dental porcelains were first introduced in the dental industry in the 1980s. Optec™ porcelain, the subject of U.S. Patent No. 4,798,536, is one example of feldspathic porcelain that has been used in the manufacture of all-ceramic dental restorations. Currently, the most common technique for manufacturing all-ceramic dental restorations is heat-pressing, also known as injection molding, of all-ceramic cores. Dental glass-ceramic materials, such as OPC® pressable ceramic and Empress® pressable ceramic, exhibit flexure strength from about 120 MPa to about 180 MPa due to a relatively high fraction of leucite crystals embedded in the glass matrix. Historically, the first leucite-containing components of dental porcelains were produced by melting potassium feldspar with fluxes as described in U.S. Patent No. 4,798,536, which is hereby incorporated by reference. Thus, these glass-ceramic materials are often also referred to as high-strength feldspathic dental porcelains or leucite-reinforced dental ceramics or glass-ceramics. The leucite content in these materials is higher than at least about 35 weight percent and most of the porcelains have a leucite content from about 45 to about 60 weight percent. As a result, they exhibit relatively high coefficients of thermal expansion (CTE) in excess of about $15 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to

500°C) and require specifically developed porcelains with a matching high thermal expansion. At the same time, most of the porcelains used for porcelain-fused-to-metal (PFM) restorations have CTEs of about 12 to about $13 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to 500°C) and are compatible with most commonly used precious and non-precious alloys having CTEs in the range of about 13 to about $15 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to 500°C). Thus, these porcelains are commonly referred to as conventional porcelains.

One of the distinct advantages of the heat-pressing (injection molding) method for fabricating all-ceramic cores is exceptionally accurate and consistent margin adaptation. Only very few and the most experienced dental technicians can achieve the same accuracy building porcelain margins by hand. The most time-consuming procedure is manual fabrication of porcelain margins on multi-unit metal frameworks for fixed partial dentures (FPD) or bridges. To circumvent these difficulties, a new method commonly referred to as "pressing to metal" was recently introduced, where a heat-pressing technique is used to press high expansion leucite-based glass-ceramic directly onto a metal framework. As a result, to produce the finished restoration, the technique requires layering the press-to-metal core with the porcelain having a coefficient of thermal expansion exceeding that of conventional porcelains.

It would be extremely beneficial to have pressable all-ceramic cores compatible with these aforementioned porcelains and at the same time capable of being directly pressed to metal.

Summary Of The Invention

These and other objects and advantages are accomplished by the pressable dental ceramic of the present invention comprising a mixture of glass and glass-ceramic frits. A refractory filler is also combined with the frits. The dental ceramic contains an amount of leucite less than about 35 percent by weight. Other additives may be included such as pigments, opacifying agents and fluorescing agents. Prior to pressing, the dental ceramic comprises a cellular-like microstructure comprised of glassy regions surrounded by clusters of leucite crystals distributed around those glassy regions forming a cellular three-dimensional network and after pressing, the dental material comprises a textured

microstructure.

In another embodiment, a pressable dental ceramic is formed by mixing and firing at least one glass frit and at least one glass-ceramic frit. Preferably, pellets or blanks are fabricated by mixing two frits, a relatively coarse glass frit and a very fine leucite-containing frit. Specifically, the average particle size of the leucite frit should be about six times smaller than the particle size of the glass frit. The pressable pellet exhibits a cellular-like microstructure comprised of glassy regions surrounded by clusters of leucite crystals distributed around those glassy regions forming a cellular three-dimensional network, which transforms into a textured microstructure upon pressing.

The pressable dental ceramics are useful for forming cores and frameworks for all ceramic dental restorations and as overlays for press-to-metal dental restorations including, but not limited to, orthodontic appliances, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connectors.

Brief Description Of The Drawings

Features of the present invention are disclosed in the accompanying drawings, wherein similar reference characters denote similar elements throughout the several views, and wherein:

FIGURE 1 is a photomicrograph of the dental ceramic prior to pressing;
FIGURE 2 is a schematic diagram of the photomicrograph of FIGURE 1;
FIGURE 3 is a photomicrograph of the dental ceramic of FIGURE 1 after

pressing;

FIGURE 4 is a schematic diagram of the photomicrograph of FIGURE 3;

FIGURE 5 shows thermal expansion curves for three different materials;

FIGURE 6 shows an enlarged view of a section of the schematic diagram shown in FIGURE 4; and

FIGURE 7 shows a magnified section of an area in the photomicrograph of FIGURE 1.

Description Of The Invention

Leucite-based glass ceramic materials of the present invention are made by a conventional heat-pressing technique, also known as injection molding, similar to procedures used to manufacture OPC[®] pressable ceramic available from Pentron Laboratory Technologies, LLC and Empress[®] pressable ceramic available from Ivoclar Corporation. In order to press cores for all-ceramic dental restorations using these conventional techniques and commercial equipment, the materials are formed into the shape of a blank or pellet. Blanks or pellets are fabricated by compacting and subsequently firing starting glass-ceramic powder comprising a mixture of various glass or glass-ceramic frits and additives such as pigments, opacifying agents and fluorescing agents. The essential feature of the present invention is that these blanks/pellets have a cellular-like microstructure comprised of glassy regions surrounded by clusters of leucite crystals distributed around those glassy regions forming a cellular three-dimensional network.

In one embodiment herein, a pressable dental ceramic pellet or blank is formed from a mixture of at least one glass frit, at least one glass-ceramic frit and at least one refractory filler. Preferably, the glass frit is present in an amount of from about 40 to about 65 percent by weight, the glass-ceramic frit is present in an amount of from about 35 to about 60 percent by weight and the refractory filler is present in an amount from about 0.5 to about 10 percent by weight. The glass-ceramic frit contains an amount of leucite of at least 60 percent by weight to provide an amount of leucite in the final dental ceramic composition of less than or equal to about 35 percent by weight.

The role of the refractory filler is two-fold. It is needed to lower the thermal expansion of the porcelain and also to impart enough resistance to distortion to enable preserving accurate fit and marginal integrity during repetitive firing of the overlay porcelain onto the dental ceramic. Normally, the difference between the pressing temperature for a pressable core and the firing temperature of the overlay porcelain is at least 150°C. By contrast, in the invention herein, the difference between the pressing temperature for the pressable core and the firing temperature of the overlay porcelain is less than about 150°C and preferably less than about 110°C. Materials of the present invention are pressable at temperatures as low as 980°C, but due to both their textured

microstructure and the presence of the refractory filler, they can withstand the firing of the overlay porcelain thereon to temperatures as high as 900°C (1652°F), which is a small difference of 80°C.

The textured microstructure provides integrity to the dental ceramic and the refractory filler prevents distortion of the dental ceramic. In order to provide optimum results, the refractory filler should have a thermal expansion lower than the thermal expansion of the frits used in the pressable core material and a refractive index within about 0.2 of the refractive index of the frits. Opacifiers, such as zirconia, titania, zirconium silicate (ultrox) and tin oxide, which are conventional additives in dental ceramic and porcelain materials are different from the refractory fillers used herein because they are used to opacify the frits and must have a refractive index that is different from the refractive index of the frits by 0.5 or greater in order to opacify. Glass and glass ceramic frits have a refractive index in the range from about 1.45 to about 1.55, which is characteristic of most conventional alumo-silicate and alumo-boro-silicate glasses. The following Table 1 provides the refractive indices of various opacifiers, glass and glass-ceramic frits and refractory fillers of the invention.

Table 1. Refractive Indices.

Material	Crystal Structure	Refractive Index	Use	Difference In RI Between Frits And Material
TiO ₂	Rutile	2.7	Opacifier	1.2
ZrO ₂	Mg-Stabilized Zirconia (Cubic And Tetragonal)	2.15	Opacifier	0.65
SnO ₂	Cassiterite	2.093	Opacifier	0.593
ZrSiO ₄		1.95	Opacifier	0.45
Al ₂ O ₃	Corundum	1.76	Opacifier	0.26
ZnO		2.01	Opacifier	0.51
Glass and Glass-Ceramic Frits		1.45 - 1.55		0
leucite		1.5		0
Cordierite		1.53	Refractory Filler	0.03
Mullite		1.64	Refractory Filler	0.14

Spinel		1.72	Refractory Filler	0.22
Alumina		1.76	Can Be Used As Refractory Filler Only In Combination With Others	0.26
Fused (amorphous) silica		1.46	Refractory Filler	0.04
Quartz (crystalline silica)		1.55	Refractory Filler	0.05

Prior to pressing the dental ceramic blank or pellet into a dental restorative material, the dental ceramic comprises a cellular-like microstructure comprised of glassy regions surrounded by clusters of leucite crystals distributed around those glassy regions forming a cellular three-dimensional network. Figures 1, 2 and 7 clearly represent this aspect of the dental ceramic.

In yet another embodiment, at least one glass frit is mixed with at least one glass-ceramic frit and sintered to form a pressable dental ceramic. Preferably, pellets are fabricated by mixing two frits, a relatively coarse glass frit and a very fine leucite-containing frit. Opacifying agents, fluorescing agents, other additives and pigments may be added to the mixture as well. The particle size distribution of the component frits are engineered specifically to ensure that during the blending of the frits and compacting the resulting mixture into the shape of pellets, the leucite frit will be coordinated into interstitial sites between much larger particles of the glass frit. Specifically, the average particle size of the leucite frit should be about six times smaller than that of the glass frit. More specifically, the average particle size (mv) of the leucite frit should be less than about 7 microns (m μ) and the average particle size (mv) of the glass frit should be more than about 35 m μ . It is most preferred that the leucite frit has an mv \leq 6 m μ and the glass frit has an mv \geq 36 m μ .

The pressing temperature of the dental ceramics discussed herein is from about 980 to about 1030°C. After pressing the dental ceramic into a mold whereby it is formed into the desired shape, it is able to withstand firing of a porcelain thereon at a range from about 830 to about 900°C without distorting the dental ceramic.

Figure 1 represents a micrograph of the microstructure of a pellet (from Example

1 below) manufactured in accordance herein comprising a three-dimensional network of
leucite arranged in a cellular pattern and Figure 2 shows a schematic diagram of the
micrograph of Figure 1. Figure 2 depicts leucite-containing sections 20 separated by
glassy, leucite-free sections 22. During pressing, the roughly equiaxed "cells" of the
5 cellular microstructure are being stretched in the direction of viscous flow and flattened
in the direction normal to the flow which results in a so-called "pancake" structure as
shown in Figures 3 and 4.

Figure 3 is a micrograph of the pellet from Figure 1 that has been pressed at
1020°C and Figure 4 is a schematic diagram of the micrograph of Figure 3. Figure 4
10 shows leucite-containing layers 40 separated by glassy, leucite-free layers 42. This
"pancake" structure is well known in metallurgy as a type of structure formed by cold-
working of metals. In the case of metals this "pancake" microstructure is formed by
plastic deformation of the originally equiaxed grains and results in a stronger metal, an
effect known as strain-hardening. In the glass-ceramic material of the present invention,
15 somewhat similar microstructural changes resulting in a pancake appearance of the
microstructural features (cells) are achieved by constrained viscous flow of the glass-
ceramic material forced through narrow channels of the refractory mold.

This coordination between particle sizes of the component frits results in a
cellular microstructure (as shown in Figures 1 and 2) in the pellet, which upon pressing
20 transforms into a "pancake" or layered type of microstructure (as shown in Figures 3 and
4). The inventor herein has found that this combination produces surprisingly high
strength and, at the same time, relatively low expansion. In the following description, the
term "layered" is used interchangeably with the term "textured" to describe the generic
type of microstructure associated with the materials described herein.

Figure 6 shows an enlarged section of individual leucite crystals from Figure 4.
The schematic diagram shown in Figure 2 would render the same depiction of individual
leucite crystals as shown in Figure 6. Figure 7 shows a magnified section of an area in
the dental ceramic shown in Figure 1. It shows individual leucite crystals that are
schematically shown in Figure 6.

The following examples illustrate the invention.

Example 1 and Comparative Example 2

To illustrate the concept of the textured microstructure, two examples were carried out having the same composition, but with different particle sizes. Two frits with compositions and properties given in Table 2 below were mixed with a small amount of an opacifier and hand-pressed into cylindrical pellets. A first glass frit (a low expansion frit) with a CTE of about $9 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to 500°C) was added as approximately 57 wt% of the mixture. A second, high expansion frit, containing about 60% to about 70% of leucite with a CTE of about $18 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to 500°C) was added as approximately 40% of the mixture. Additionally, about 3 wt% of Al_2O_3 was added as a refractory filler (alumina is used for the sake of illustration of the concept since it has refractive index that is a bit too high to use in substantial quantity without over opacifying the material). The high expansion frit was fabricated in two particle size variations, fine with average particle size of about $6 \mu\text{m}$ and coarse with average particle size of about $18 \mu\text{m}$. The fine frit was used in Example 1 and the coarse frit was used in comparative Example 2. The same glass frit with an average particle size of about $33 \mu\text{m}$ was used in both examples. Component frits and alumina were mixed and dry-pressed into small cylindrical pellets weighing approximately 2 grams each. Pellets of Example 1 and Example 2 were fired in vacuum to full density using the same firing cycle. Various dental articles as well as rods for 3-pt bending were pressed into refractory molds made from Universal™ Investment material using a conventional pressing technique in the AutoPress® Plus pressing furnace (available from Pentron Laboratory Technologies, LLC) at 1020°C . Rods were tested in 3-pt bending equipment. The material of Example 1 with the layered pancake microstructure exhibited a flexure strength of $137 \pm 12 \text{ MPa}$ and the material from comparative Example 2 having an equiaxed microstructure exhibited a flexure strength of $92 \pm 5 \text{ MPa}$.

Table 2. Component frit compositions and properties

	Glass Frit	Leucite Frit	Overall Composition of Example 1 and Comparative Example 2
CTE@ 500°C , ppm= $10^{-6} (^{\circ}\text{C})^{-1}$	9	18	13.3
Glass Transition Temperature	600	650	610

Average particle size, μm	33	6 (Example 1) 18 (Example 2)	
SiO ₂	67.93	65.01	64.69
B ₂ O ₃	0.00	0.00	0
Al ₂ O ₃	13.35	18.01	17.79
ZnO	0.00	0.00	0
CaO	1.99	0.77	1.44
MgO	0.00	0.00	0
BaO	0.00	0.00	0
Li ₂ O	0.00	0.51	0.2
K ₂ O	10.16	13.89	11.34
Na ₂ O	6.18	1.81	4.24
TiO ₂	0.00	0.00	0
ZrO ₂	0.00	0.00	0
CeO ₂	0.40	0.00	0.28

Example 3

The same glass as the one used in Examples 1 and 2 in Table 2 above was milled to yield a glass (a low expansion) frit with an average particle size of 36 μm . The high expansion frit of Examples 1 and 2 was combined with a second high expansion frit in the weight ratio of from 1:1 to 1:1.5. Both high expansion frits had a particle size of about 6 μm . The mixture of the two high expansion frits was combined with the glass frit in the ratio of about 1:1. Additionally, about 2 wt% of Al₂O₃ and about 2 wt% of fused silica were added to lower the thermal expansion of the mixture of the frits and to impart sufficient resistance to distortion to enable firing of the overlay porcelain at temperatures up to about 890°C.

Table 3. Overall composition of Example 3 and Example 1 & 2 from above.

Overall composition, wt%	Examples 1&2	Example 3	Frits Used in Example 3		
			Glass Frit	First Leucite Frit	Second Leucite Frit
SiO ₂	64.69	65.37	67.39	65.01	63.82
B ₂ O ₃	0.00	0.00	0.00	0.00	0.00
Al ₂ O ₃	17.79	17.03	13.35	18.01	17.69

ZnO	0.00	0.00	0.00	0.00	0.00
CaO	1.44	1.30	1.99	0.77	0.76
MgO	0.00	0.00	0.00	0.00	0.00
BaO	0.00	0.00	0.00	0.00	0.00
Li2O	0.20	0.67	0.00	0.51	1.88
K2O	11.34	11.54	10.16	13.89	13.67
Na2O	4.24	3.74	6.18	1.81	1.77
TiO2	0.00	0.00	0.00	0.00	0.00
ZrO2	0.00	0.00	0.00	0.00	0.00
CeO2	0.28	0.35	0.40	0.00	0.41

Pellets were fabricated as described in Examples 1 and 2 above. Heat-pressing was carried out at 990°C using the same equipment and procedures as in the previous examples. A plastic rod with a length of 63 mm was invested in a 300 g investment ring.

- 5 Following burn-out, pressing and divesting, the as-pressed rod was cut to 51 mm and used to measure thermal expansion from room temperature to 700°C. The CTE was measured as $13.6 \times 10^{-6}/^{\circ}\text{C}$ and $14.0 \times 10^{-6}/^{\circ}\text{C}$ (from room temperature to 500°C and to 600°C, respectively), and the GTT was $570^{\circ}\text{C} \pm 20^{\circ}\text{C}$ measured at as-pressed condition. Figure 5 shows thermal expansion curves of the pressed glass-ceramics of Examples 1 and 3 overlaid with thermal expansion curves of Avante Micro Crystal® body and incisal porcelain. Some of the pressed samples were sectioned, mounted, polished and etched for microscopic examination to confirm the presence of a textured microstructure as shown in Figures 3 and 4.

15

Example 4

Strength, Weibull Modulus And Compatibility With Porcelain-Fused-To-Metal (PFM) Porcelain

- 20 A mixture of frits used in Example 3 and fused silica was shaded by using about 1% of commercially available pigments. Pellets were fabricated as described above in the previous examples. Various dental articles and various test specimens including 24 rods for a 3-pt bend test were pressed at 1000°C using the equipment and procedures described above. Following normal divesting procedures, as-pressed rods of about 20 mm in length and about 3.3 mm in diameter were loaded to failure in three-point bending configuration. Three-point flexure strength was determined to be 142 MPa with a

standard deviation as low as 12 MPa (8.4%). In addition, the measured strength values were ranked and used to calculate the Weibull modulus (m). An extremely high Weibull modulus of 13.6 and a Weibull strength value (σ_0) of 146.9 MPa with the correlation factor (R^2) of 0.95 were established for this material. Based on the determined Weibull parameters, a stress value corresponding to the survival probability of 99.9%, ($\sigma_{99.9\%}$) (representing the case when only one specimen in 1000 fails) was calculated to be 88.5 MPa. Both values for Weibull modulus (m), and $\sigma_{99.9\%}$ were surprisingly high compared to values for leucite-containing, lithium disilicate and glass infiltrated dental ceramics known from the literature (H. Fisher, M. Weber, and R. Marx, Lifetime Prediction of All-ceramic Bridges by Computational Methods, *J Dent Res* 82 (3): 238-242, 2003) which is hereby incorporated by reference and which results are summarized in Table 4 below. Most important, the $\sigma_{99.9\%}$ of 88.5 MPa was substantially higher than the maximum principal stress of 72 MPa associated with peak loads produced during the normal masticating process. This data indicates the specific benefits associated with a type of microstructure, termed layered or textured, characteristic for glass-ceramic materials of this invention. The leucite-based glass-ceramics of this invention having leucite content of less than 35% still exhibits strength comparable to leucite-reinforced dental ceramics such as Empress[®] and OPC[®] which have higher leucite content. At the same time, in reliability, it matches much stronger and tougher ceramic materials such as some lithium disilicate and glass infiltrated ceramics (see Fisher et al. for m values for these materials).

Table 4. Data from Fisher Article and from Example 3 herein.

Material	Type of Glass-Ceramic	Elastic Modulus GPa	Poisson's Ration ν	σ_0 MPa	Weibull Modulus m	Calculated $\sigma_{99.9\%}$	$\sigma_{1,max}$ MPa @ 600 N load	Reliability Factor = $\sigma_{99.9\%} / \sigma_1$
Empress [®] 1*	leucite	67	0.19	89	8.6	40	72	0.55
Empress [®] 2*	lithium-disilicate	96	0.22	289	8.8	132	85	1.55
InCeram [™] Alumina**	glass-infiltrated	251	0.22	290	4.6	65	130	0.50
3Y-SZ [™] ***	YTZP zirconia	205	0.31	937	18.4	644	125	5.15
Example 3	leucite	70	0.2	146.9	13.6	88	72	1.23

*IVOCLAR AG CORPORATION

**VITA ZAHNFABRIK H. RAUTER GMBH & CO.

***METOXIT AG

A number copings and nearly full contour crowns were pressed at temperatures of varying from 980°C to 1000°C to evaluate fit and absence of distortion from both white (unshaded) and shaded material. The pressed copings were layered with Avante Microcrystal[®] porcelain (Pentron) and d.SIGN[®] porcelain (Ivoclar). Both porcelains are currently used to fabricate PFM restorations using alloys with a CTE of about $13-15 \times 10^{-6}/^{\circ}\text{C}$. Porcelains were fired at temperatures of varying from 830°C to 900°C with grinding and the addition of new porcelain for up to four times. No distortion, cracking, crazing or discoloration was observed.

A standard master die was used to design a standard framework for a 4-unit posterior bridge with up to 4 mm long margins. This standard framework was duplicated in a variety of metals including Rexillum III[®], Rexillum[®] V, REX 4[®], REX CC[®] and Avante MicroFine[™] 50, 60, 68, 76 alloys and Rx G-Universal. Following application of two coats of Avante[®] Opaque these frameworks were invested in 300 g rings often together with wax-ups for all-ceramic single units. Shaded pellets of the glass-ceramic composition of Example 3 were pressed at 1000°C. Following standard divesting and cleaning procedures the press-to-metal bridges were layered with Avante Microcrystal[®] and d.SIGN[®] porcelains and fired with grinding and addition of new porcelain for up to four times. No distortion, cracking, crazing or discoloration was observed.

The essential feature of the glass-ceramic material of this invention is its engineered microstructure that results in a relatively high strength at low leucite content and therefore a relatively low CTE in the range of 12.5 – 14.5 ppm. As a result, all-ceramic cores made from this material are compatible with some porcelains used in PFM restorations fabricated on a wide range of popular and commonly used alloys having a CTE in the range of 13 – 15 ppm. The material of the present invention can be pressed onto metal directly.

While various descriptions of the present invention are described above, it should be understood that the various features can be used singly or in any combination thereof. Therefore, this invention is not to be limited to only the specifically preferred embodiments depicted herein.

Further, it should be understood that variations and modifications within the spirit and scope of the invention may occur to those skilled in the art to which the invention pertains. Accordingly, all expedient modifications readily attainable by one versed in the art from the disclosure set forth herein that are within the scope and spirit of the present invention are to be included as further embodiments of the present invention. The scope of the present invention is accordingly defined as set forth in the appended claims.

10

15

20

25

30

Claims

What Is Claimed Is:

1. A pressable dental ceramic comprising:
5 a glass frit;
a glass-ceramic frit comprising leucite; and
a refractory filler having a thermal expansion lower than the thermal expansion of
the frits and a refractive index within ± 0.2 of the refractive index of the frits;
wherein leucite is present in the dental ceramic in an amount less than about 35%
10 by weight;
wherein the thermal expansion of the dental ceramic is in the range of about $12.5 \times 10^{-6}/^{\circ}\text{C}$ to about $14.5 \times 10^{-6}/^{\circ}\text{C}$ measured from room temperature to 500°C ;
wherein the dental ceramic is pressable from about 980°C to about 1030°C ; and
wherein the dental ceramic can withstand firing of a porcelain onto the dental
15 ceramic without distortion of the dental ceramic at a range from about 830°C to about 900°C .
2. The pressable dental ceramic of claim 1 wherein the refractory filler is
selected from the group consisting of silica, cordierite, mullite, alumina, spinel, and
20 mixtures thereof.
3. The pressable dental ceramic of claim 2 wherein the silica is amorphous
silica and is selected from the group consisting of fused silica, fumed silica and mixtures
thereof.
25
4. The pressable dental ceramic of claim 1 having a cellular-like
microstructure in a prior to pressing and a layered microstructure comprising leucite-rich
layers separated by glass-rich layers after pressing.

5. A dental restoration for placement in a person's mouth comprising the pressable dental ceramic of claim 4 wherein the leucite-rich layers and glass-rich layers are oriented normal to the direction of the mastication loads in a person's mouth.
- 5 6. The pressable dental ceramic of claim 1 wherein the refractive index of the glass and glass-ceramic frits and the refractive index of the refractory filler are substantially the same or within about ± 0.2 of one another.
7. The pressable dental ceramic of claim 1 wherein the glass frit has a glass
10 transition temperature $\geq 580^\circ\text{C}$.
8. The pressable dental ceramic of claim 1 wherein the glass-ceramic frit has a glass transition temperature $\geq 600^\circ\text{C}$.
- 15 9. The pressable dental ceramic of claim 1 wherein the glass frit has an average particle size equal to or greater than about six times the average particle size of the glass-ceramic frit.
10. The pressable dental ceramic of claim 10 wherein the glass frit has an
20 average particle size of equal to or greater than about 35 microns and the glass-ceramic frit has an average particle size of equal to or less than about 6 microns.
11. The pressable dental ceramic of claim 1 further comprising a second glass-ceramic frit.
- 25 12. The pressable dental ceramic of claim 1 having a three-point bend strength measured per ISO 6872 standard equal to higher than 130 MPa.
13. The pressable dental ceramic of claim 1 having a three-point bend strength
30 measured per ISO 9693 standard equal to higher than 130 MPa.

14. The pressable dental ceramic of claim 1 further comprising one or more of a pigment, opacifying agent and fluorescing agent.

15. The pressable dental ceramic of claim 1 wherein the glass frit is present in an amount from about 40 to about 65 percent by weight, the glass-ceramic frit is present in an amount from about 35 to about 60 percent by weight and the refractory filler is present in an amount from about 0.5 to about 10 percent by weight.

16. A dental restoration comprising;
a pressed core comprising a dental ceramic comprising a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler having a thermal expansion lower than the thermal expansion of the frits and a refractive index within ± 0.2 of the refractive index of the frits, wherein leucite is present in the dental ceramic in an amount less than about 35% by weight, and wherein the thermal expansion of the dental ceramic is in the range of about $12.5 \times 10^{-6}/^{\circ}\text{C}$ to about $14.5 \times 10^{-6}/^{\circ}\text{C}$ measured from room temperature to 500°C , wherein the dental ceramic is pressable from about 980°C to about 1030°C , and wherein the dental ceramic can withstand firing of a porcelain onto the dental ceramic without distortion of the dental ceramic at a range from about 830°C to about 900°C ; and a porcelain overlay on the pressed core having a maturing temperature higher than about 830°C .

17. A dental restoration comprising;
a pressed core comprising a dental ceramic comprising a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler having a thermal expansion lower than the thermal expansion of the frits and a refractive index within ± 0.2 of the refractive index of the frits, wherein leucite is present in the dental ceramic in an amount less than about 35% by weight, and wherein the thermal expansion of the dental ceramic is in the range of about $12.5 \times 10^{-6}/^{\circ}\text{C}$ to about $14.5 \times 10^{-6}/^{\circ}\text{C}$ measured from room temperature to 500°C , wherein the dental ceramic is pressable from about 980°C to about 1030°C , and wherein the dental ceramic can withstand firing of a porcelain onto the dental ceramic without distortion of the dental ceramic at a range from about 830°C to about 900°C ; and

a porcelain overlay on the pressed core having a maturing temperature higher than about 830°C;

wherein the difference between the pressing temperature of the core and the firing temperature of the overlay is less than 150°C.

5

18. The dental restoration of claim 17 wherein the difference between the pressing temperature of the core and the firing temperature of the overlay is less than 110°C.

10

19. A pressable dental ceramic comprising a:

a glass frit;

a glass-ceramic frit comprising leucite; and

a refractory filler;

wherein the glass frit has an average particle size equal to or greater than about

15 six times the average particle size of the glass-ceramic frit.

20

20. The pressable dental ceramic of claim 19 wherein the glass frit is present in an amount from about 40 to about 65 percent by weight, the glass-ceramic frit is present in an amount from about 35 to about 60 percent by weight and the refractory filler is present in an amount from about 0.5 to about 10 percent by weight.

25

21. The pressable dental ceramic of claim 19 wherein the glass frit has an average particle size of equal to or greater than about 35 microns and the glass-ceramic frit has an average particle size of equal to or less than about 6 microns.

22. The pressable dental ceramic of claim 19 having a cellular microstructure prior to pressing and a textured microstructure after pressing.

30

23. The pressable dental ceramic of claim 19 having a three-point bend strength measured per ISO 6872 standard equal to higher than 130 MPa.

24. The pressable dental ceramic of claim 19 having a three-point bend strength measured per ISO 9693 standard equal to higher than 130 MPa.

25. The pressable dental ceramic of claim 19 wherein the leucite content of the dental ceramic is less than 35 percent by weight.

26. The pressable dental ceramic of claim 19 wherein the dental ceramic is pressable from about 980 to about 1030°C, and wherein the dental ceramic can withstand firing of a porcelain onto the dental ceramic without distortion of the dental ceramic at a range from about 830 to about 900°C.

27. A dental restoration comprising:
a pressed core comprising a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler, wherein the glass frit has an average particle size equal to or greater than about six times the average particle size of the glass-ceramic frit; and
a porcelain overlay on the pressed core having a maturing temperature higher than about 830°C.

28. The dental restoration of claim 27 wherein the pressed core has a textured microstructure.

29. A press-to-metal dental restoration comprising:
a metal framework;
a pressed ceramic overlay, wherein the ceramic overlay comprises a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler having a thermal expansion lower than the thermal expansion of the frits and a refractive index within ± 0.2 of the refractive index of the frits, wherein leucite is present in the dental ceramic in an amount less than about 35% by weight, and wherein the thermal expansion of the dental ceramic is in the range of about 12.5 to about 14.5 measured from room temperature to 500°C, wherein the dental ceramic is pressable from about 980 to about 1030°C, and wherein the

dental ceramic can withstand firing of a porcelain onto the dental ceramic without distortion of the dental ceramic at a range from about 830 to about 900°C; and

a porcelain overlay on the pressed ceramic having a maturing temperature higher than about 830°C.

5

30. A press-to-metal dental restoration comprising:
a metal framework;

10 a pressed ceramic overlay, wherein the ceramic overlay comprises a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler, wherein the glass frit has an average particle size equal to or greater than about six times the average particle size of the glass-ceramic frit; and

a porcelain overlay on the pressed ceramic having a maturing temperature higher than about 830°C.

15 31. The dental restoration of claim 5 selected from the group consisting of orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

20 32. The dental restoration of claim 16 selected from the group consisting of orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

25 33. The dental restoration of claim 17 selected from the group consisting of orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

30 34. The dental restoration of claim 19 selected from the group consisting of orthodontic appliances, overlays, bridges, space maintainers, tooth replacement

appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

35. The dental restoration of claim 27 selected from the group consisting of
5 orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

36. The dental restoration of claim 29 selected from the group consisting of
10 orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

37. The dental restoration of claim 30 selected from the group consisting of
15 orthodontic appliances, overlays, bridges, space maintainers, tooth replacement appliances, splints, crowns, partial crowns, dentures, posts, teeth, jackets, inlays, onlays, facing, veneers, facets, implants, abutments, cylinders, and connector.

38. A method of making a dental restoration comprising:
20 heating a ceramic pellet or blank to a temperature in the range from about 980°C to about 1030°C and pressing the ceramic pellet or blank, wherein the ceramic pellet or blank comprises a dental ceramic comprising a glass frit, a glass-ceramic frit comprising leucite, and a refractory filler having a thermal expansion lower than the thermal expansion of the frits and a refractive index within ± 0.2 of the refractive index of the
25 frits, wherein leucite is present in the dental ceramic in an amount less than about 35% by weight, and wherein the thermal expansion of the dental ceramic is in the range of about $12.5 \times 10^{-6}/^{\circ}\text{C}$ to about $14.5 \times 10^{-6}/^{\circ}\text{C}$ measured from room temperature to 500°C, into a mold space that has been placed in a pressing furnace, whereby the ceramic pellet conforms to the mold space to form a ceramic core;
30 removing the ceramic core from the mold space;

applying and shaping a dental porcelain powder onto the ceramic core; and
heating the shaped dental porcelain powder to a temperature in the range from
about between about 830°C to about 900°C to fuse the dental porcelain powder to the
ceramic core.

5

39. The method of claim 38 wherein the porcelain has a coefficient of thermal
in the range of about $12.0 \times 10^{-6}/^{\circ}\text{C}$ to about $14.0 \times 10^{-6}/^{\circ}\text{C}$ in the temperature range of
25°C. to 500°C.

10

40. A method of making a dental restoration comprising:
forming a metal framework;

heating a ceramic pellet or blank to a temperature in the range from about 980°C
to about 1030°C and pressing the ceramic pellet or blank, wherein the ceramic pellet or
blank comprises a dental ceramic comprising a glass frit, a glass-ceramic frit comprising
leucite, and a refractory filler having a thermal expansion lower than the thermal
expansion of the frits and a refractive index within ± 0.2 of the refractive index of the
frits, wherein leucite is present in the dental ceramic in an amount less than about 35% by
weight, and wherein the thermal expansion of the dental ceramic is in the range of about
 $12.5 \times 10^{-6}/^{\circ}\text{C}$ to about $14.5 \times 10^{-6}/^{\circ}\text{C}$ measured from room temperature to 500°C, onto
the metal framework to form a ceramic overlay;

15

20

applying and shaping a dental porcelain powder onto the ceramic overlay; and
heating the shaped dental porcelain powder to between about 830°C to
about 900°C to fuse the dental porcelain powder to the ceramic core.

25

41. The method of claim 40 wherein the metal framework comprises a
precious,
semiprecious or non-precious alloy.

30

42. The method of claim 40 wherein metal framework is produced by casting,
powder metallurgy or rapid prototyping techniques.

43. The method of claim 42 wherein the casting comprises capillary casting.

44. A method of making a dental restoration comprising:

heating a ceramic pellet or blank to a temperature in the range from about 980°C
5 to about 1030°C and pressing the ceramic pellet or blank, wherein the ceramic pellet or
blank comprises a dental ceramic comprising a glass frit, a glass-ceramic frit comprising
leucite, and a refractory filler having a thermal expansion lower than the thermal
expansion of the frits and a refractive index within ± 0.2 of the refractive index of the
frits, wherein leucite is present in the dental ceramic in an amount less than or equal to
10 about 35% by weight, wherein the thermal expansion of the dental ceramic is in the range
of about 12.5 to about 14.5 measured from room temperature to 500°C, whereby the
ceramic pellet conforms to the mold space to form a ceramic core;

removing the ceramic core from the mold space;

applying and shaping a dental porcelain powder onto the ceramic core; and

15 heating the shaped dental porcelain powder to a temperature in the range from
about between about 830°C to about 900°C to fuse the dental porcelain powder to the
ceramic core.

45. A method of making a dental restoration comprising:

20 forming a metal framework;

heating a ceramic pellet or blank to a temperature in the range from about 980°C
to about 1030°C and pressing the ceramic pellet or blank, wherein the ceramic pellet or
blank comprises a dental ceramic comprising a glass frit, a glass-ceramic frit comprising
leucite, and a refractory filler having a thermal expansion lower than the thermal
25 expansion of the frits and a refractive index within ± 0.2 of the refractive index of the
frits, wherein leucite is present in the dental ceramic in an amount less than or equal to
about 35% by weight, wherein the thermal expansion of the dental ceramic is in the range
of about 12.5 to about 14.5 measured from room temperature to 500°C, onto the metal
framework to form a ceramic overlay;

30 applying and shaping a dental porcelain powder onto the ceramic overlay; and

heating the shaped dental porcelain powder to between about 830°C to

about 900°C to fuse the dental porcelain powder to the ceramic core.

46. The method of claim 45 wherein the metal framework comprises a precious, semiprecious or non-precious alloy.

5

47. The method of claim 45 wherein metal framework is produced by casting, powder metallurgy or rapid prototyping techniques.

48. The method of claim 47 wherein the casting comprises capillary casting.

10

15

20

25

30

THIS PAGE BLANK (USPTO)

1/5




FIG. 1

THIS PAGE BLANK (USPTO)

2/5




FIG. 2




FIG. 4




FIG. 6

THIS PAGE BLANK (USPTO)

3/5




FIG. 3

THIS PAGE BLANK (USPTO)




FIG. 5

THIS PAGE BLANK (USPTO)

5/5




FIG. 7

THIS PAGE BLANK (USPTO)

INTERNATIONAL SEARCH REPORT

Internati application No
PCT/US 03/33018

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 245 548 A (YAMAMOTO PRECIOUS METAL CO LTD) 2 October 2002 (2002-10-02) paragraphs '0039!-'0050! examples claims 1-11	1-48
P, X	EP 1 329 430 A (IVOCLAR VIVADENT AG) 23 July 2003 (2003-07-23) paragraphs '0011!', '0018!', '0019!', '0025!', '0029! examples claims 1-16	1-48
X	US 6 120 591 A (KAISER LISA ET AL) 19 September 2000 (2000-09-19) column 3, line 15 - line 53 claims 1-25	1-48
X	WO 99 45889 A (JENERIC PENTRON INC) 16 September 1999 (1999-09-16) the whole document	1-48
A	WO 01 01925 A (JENERIC PENTRON INC) 11 January 2001 (2001-01-11)	
A	EP 0 152 338 A (SUISSOR SA) 21 August 1985 (1985-08-21)	
A	EP 0 690 030 A (IVOCLAR AG) 3 January 1996 (1996-01-03)	
A	HOELAND W ET AL: "NEEDLE-LIKE APATITE-LEUCITE GLASS-CERAMIC AS A BASE MATERIAL FOR THE VENEERING OF METAL RESTORATIONS IN DENTISTRY" JOURNAL OF MATERIALS SCIENCE. MATERIALS IN MEDICINE, CHAPMAN AND HALL, LONDON, GB, vol. 11, no. 1, 1 January 2000 (2000-01-01), pages 11-17, XP001008969 ISSN: 0957-4530	

INTERNATIONAL SEARCH REPORT

international application no
PCT/US 03/33018

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61K6/06 C03C10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 A61K C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, BIOSIS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 253 116 A (ELEPHANT DENTAL BV) 30 October 2002 (2002-10-30) paragraphs '0010!'-'0012!', '0028!', '0029!', '0033!'-'0038!', '0051!', '0052! examples 1,2 claims 1-10	1-48
X	EP 1 000 588 A (DEGUSSA ;DUCERA DENTAL GMBH U CO KG (DE)) 17 May 2000 (2000-05-17) paragraphs '0013!'-'0029! examples 1-10 claims 1-11	1-48

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family.

Date of the actual completion of the international search

8 March 2004

Date of mailing of the international search report

15/03/2004

Name and mailing address of the ISA
European Patent Office, P.B. 5618 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Paloniemi Legland, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 03/33018

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1253116	A	30-10-2002	NL 1017895 C2	22-10-2002
			EP 1253116 A1	30-10-2002
			JP 2003048770 A	21-02-2003
			US 2002198093 A1	26-12-2002
EP 1000588	A	17-05-2000	DE 19852516 A1	25-05-2000
			BR 9905363 A	29-08-2000
			CA 2289820 A1	13-05-2000
			EP 1000588 A2	17-05-2000
			JP 2000139953 A	23-05-2000
			KR 2000035414 A	26-06-2000
			US 6342302 B1	29-01-2002
EP 1245548	A	02-10-2002	JP 2001192262 A	17-07-2001
			AU 2406001 A	16-07-2001
			EP 1245548 A1	02-10-2002
			WO 0149632 A1	12-07-2001
			US 2003056692 A1	27-03-2003
EP 1329430	A	23-07-2003	DE 4428839 A1	08-02-1996
			AT 244208 T	15-07-2003
			AU 699101 B2	19-11-1998
			AU 2722795 A	15-02-1996
			CA 2154990 A1	02-02-1996
			DE 59510733 D1	07-08-2003
			EP 1329430 A2	23-07-2003
			EP 0695726 A1	07-02-1996
			US 5618763 A	08-04-1997
US 6120591	A	19-09-2000	AU 2996199 A	27-09-1999
			AU 3074799 A	27-09-1999
			EP 0984765 A2	15-03-2000
			EP 0984766 A2	15-03-2000
			WO 9945888 A2	16-09-1999
			WO 9945889 A2	16-09-1999
			US 6155830 A	05-12-2000
WO 9945889	A	16-09-1999	US 6120591 A	19-09-2000
			US 6155830 A	05-12-2000
			AU 2996199 A	27-09-1999
			AU 3074799 A	27-09-1999
			EP 0984765 A2	15-03-2000
			EP 0984766 A2	15-03-2000
			WO 9945888 A2	16-09-1999
			WO 9945889 A2	16-09-1999
WO 0101925	A	11-01-2001	EP 1189572 A1	27-03-2002
			JP 2003503431 T	28-01-2003
			WO 0101925 A1	11-01-2001
			US 2003122270 A1	03-07-2003
			US 6428614 B1	06-08-2002
EP 0152338	A	21-08-1985	FR 2559386 A1	16-08-1985
			AT 44455 T	15-07-1989
			CA 1251305 A1	21-03-1989
			DE 3571390 D1	17-08-1989
			DK 69385 A	16-08-1985
			EP 0152338 A2	21-08-1985

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US 03/33018

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0152338	A	ES 8601678 A1	01-03-1986
		IE 850290 L	15-08-1985
		IE 850291 L	15-08-1985
		JP 60195033 A	03-10-1985
EP 0690030	A	DE 4423793 C1	22-02-1996
	03-01-1996	AT 152701 T	15-05-1997
		AU 677122 B2	10-04-1997
		AU 2176195 A	25-01-1996
		CA 2153130 A1	02-01-1996
		DE 59500223 D1	12-06-1997
		EP 0690030 A1	03-01-1996
		JP 2703520 B2	26-01-1998
		JP 8040746 A	13-02-1996
		US 5698019 A	16-12-1997